



SAB7 €. 18,00



SAB5 €. 16,00

Product description:

Siliceous sand washed, centrifuged, dried and selected.

Granulometry: from 350 to 1150 μ .

Security: the product is not dangerous.

Package: Cans of 5 Kg and of 7 Kg

Applications:

- Suitable for sandblasting when it's necessary strong abrasion and depth to improve paints and plasters fixing etc.
- Suitable for packaging of premixed mortars and plasters.

Characteristics and Informations of construction aggregates.

Characteristics/Specification	UNI EN 12620 Concrete aggregates	UNI EN 13139 Mortar aggregates
Granulometry	0/1 μ m	0/1 μ m
	Gf85	–
	–	Passing (% peso)
	S.1	99
	S.0,250	2
Granules volumetric mass	2,69 Mg/m ³	2,69 Mg/m ³
	S.0,063	0,1
Water absorption	0,7%	0,7%
Heap volumetric mass	1,47 Mg/m ³	1,47 Mg/m ³
Fines quality	Quantity <3%	Quantity <3%
Fines content	f ₃	Class 2
Chlorides content	0,0013%	0,0013%
Acid-soluble sulfate content	AS _{0,2}	AS _{0,2}
Total sulphur content	Quantity <1%	Quantity <1%
Alkali-silica reactivity	Not reactive	Not reactive
Petrography classification	Heterogeneous sand silicate's compound head (sandstone, rock, magma, shingle, quartz, plagioclase) and subordinate calcareous' compound (limestone).	

SPIRALFLEX S.r.l.

Via O. Simoni, 3/d – Fraz. Lavino di Mezzo
40011 ANZOLA DELL' EMILIA – BOLOGNA
Tel. 051.733.822 – Fax. 051.731.902

E-mail: info@spiralflex.com – Sito Internet: www.spiralflex.com